

**PRODUCT DESCRIPTION**

**UKB Urethane Kandy Basecoat Series (UKB)**

Is a unique product that combines our state-of-the-art, Kustom basecoat system with our high performance Kandy Koncentrate creating a ready to use Kandy basecoat that can be applied over metallic or pearls bases. **UKB** is mixed in a standard concentration that allows for uniform kandy applications in three coats. **UKB** can also be let down to lower concentrations by adding UBC825 Mid-Coat Clear base, or increased in concentration by adding **UKK** Kandy Koncentrate. UKB is available in 18 outstanding colors..

**APPLICATION**

**For Air Spray**

- Spray 2 - 3 medium-wet coats with an overlap of 50% until full hiding is achieved
- Allow 5-10 minutes @ 70° F flash time between coats
- Dry mils 2.0 to 3.0 mils. Wet mils 4.0 to 6.5 mils.
- Surface temperature should be 50-100°F with less than 80% ambient humidity preferred.

**DRY TIME**

**POT LIFE.....**When properly covered at 77°F UB Basecoat will maintain a sprayable viscosity indefinitely

**FLASH / DRY TIMES.....AIR DRY @ 77°F**

Flash Between Coats.....5-10 Minutes  
To Tape.....20-40 Minutes  
To Clearcoat.....30 Minutes

**Note:** If the basecoat is allowed to dry more than 24 hours, it must be scuffed and new basecoat applied.

**Clear Coating: KC210** Urethane Speed Clear with **KH212** Overall Hardener or **KC310** Super Flow Polyurethane Clear with **KH311** Hardener.

**MIXING / THINNING**

**Mixing Ratios: 2 : 1**

**2 parts UBC Color – 1 part KR Reducer.**

**SUBSTRATES**

**(PCB) Series Urethane Basecoat maybe applied over:**

- Cleaned, sanded and primed OEM or Refinish topcoat.
- Kustom Shop **KEP** Epoxy Primer / Sealer.
- Kustom Shop **KUP** Urethane Primer.
- Kustom Shop **KFP** Hi-Build 2K Primer Surfacer
- Kustom Shop **KPP** Polyester Primer, Kustom Shop
- Kustom Shop **KL611** Old school Acrylic Lacquer Primer.

- Epoxy Primer
- Properly Prepared OEM Surface
- Properly Prepared Aluminum and Steel.

**SURFACE PREPARATION**

**USE RECOMMENDED UNDERCOAT SYSTEM FOLLOWING RECOMMENDED PROCEDURES.**

- Wipe with KW901 Grease and Wax Remover or KW902 Anti-Static Panel Kleaner
- Abrade with 220 grit then 400 grit sandpaper or equivalent.
- Wipe again with KW901 Grease and Wax Remover or KW902 Anti-Static Panel Kleaner
- For best results apply anti-corrosive primer such as KEP Series epoxy primers over bare metal.

**EQUIPMENT CLEANING**

Clean spray guns and coating application equipment in an enclosed equipment cleaner. Use KT-912 Compliant Solvent. Follow your local air quality regulations for solvent VOC requirements.

**TECHNICAL DATA**

**VOC (Volatile Organic Content).....5.69 lbs/gal (682 g/l)**  
**VOC KR Reducers.....7.52 lbs/gal (902 g/l)**  
**VOC KR70 Reducers.....0.00 Exempt**  
**Flash Point .....27°F**



**NOTE:**



Before using any Kustom Shop product, be sure to read all MSDS and application instructions and warnings. Always wear a properly fitted air purifying respirator with organic vapor cartridges and particulate filter or a fresh air respirator (depending on product selection), eye protection, gloves and protective clothing during application and until vapors are exhausted. Do not permit anyone without protection in the painting area. This product is intended for use by a professionally trained painter.  
**Keep out of the reach of children.**